

ISSN 2348 - 8034 Impact Factor- 5.070

GLOBAL JOURNAL OF **E**NGINEERING **S**CIENCE AND **R**ESEARCHES INFLUENCE OF ACID MODIFICATION IN ASPHALT LAYER WHEN REINFORCED WITH GLASS FIBRE

Karishma Padhy^{*1} & Dr. A. Ramesh²

^{*1}PG student, Civil Engineering Department, Hyderabad ,India ²Associate Professor, Civil Engineering Department, Hyderabad ,India

ABSTRACT

The progressive traffic load intensity with its volume and tyre pressure showed a huge changes in structural stability of pavements and had resulted in pavement failure. Failure in structure is observed in the form of rutting or fatigue, to overcome from these failure number of effort were made in the past to improve the structural properties of hot mix asphalt layer using additives, chemicals etc. In this study an attempt is made to evaluate the behaviour of acid modification with the inclusion of glass fibre. The modified binder has shown better performance in $G^*/\sin\delta$ and $G^*\sin\delta$ value when compared with conventional mix. The inclusion of glass fibre in modified mix showed a beneficial improvement on performance characteristics at an optimum of 2.7%.

Keywords: PPA (Polyphosporic acid), Fibre, Rutting, Fatigue.

I. INTRODUCTION

Highway pavement is a structure consists of different layers with processed materials whose main function is to distribute vehicle load to subgrade. It essentially comprises of black-top sheet and mineral totals. HMA is the composite material comprising of total fragment with various sizes, a black-top fastener and air voids. At the point when mineral totals are bound with black-top cover, it goes about as stone system that gives quality and durability to the mix .Asphalt pavements crack due to heavy traffic loads, and the pavement surface experiences wear and tear due to various climatic conditions in addition to heavy traffic loads. The load carrying capacity is mainly based on the base, structural and friction courses of the pavement. Therefore, the aggregates should be hard enough to resist abrasion. Pavement failure occurs when an asphalt surface no longer holds its original shape and develops material stress which causes issues. Pavement major failure are rutting and fatigue, so it is essential to reduce ruts and cracks in flexible pavement layers. So each pavement material which is being used in a construction should generally have balanced design between the rutting and fatigue modes of distress. The increased rutting or decreased fatigue life of the flexible pavements may be directly affecting the service life of pavement. Depressions which along wheel path due to heavy wheel loads results in rutting failure. Fatigue is caused by failure of the surface layer or base due to excessive application of repeated wheel load. To improve the characteristics properties of payment layer and protect the HMA layer from failures modification of binders and mixes is carried out. One among the measures of binder modification with the addition of PPA and reinforcement with fibre. Abdul (2015) studied on acid modified bituminous mixes and explained that PPA addition improves rutting resistance. Sowjanya (2017) examined on performance of bituminous mixes using the bitumen, modified with polyphosphoric acid. Jack Federal Highway Administration demonstrates the impact of expanding dimensions of acid modification on dampness affectability.In thefibre-bitumen composites, bitumen can be called the matrix material, the characteristics of which are changed by using fibres in this matrix as stabilizing additives. Characteristics.Fan, (2012), outcomes demonstrated that the enhancement impacts for Marshall record are exceptional by expansion of fiber, and contrasted with polyester fiber andxylogen fiber, the enhancement impacts of basalt fiber is better. Suresh (2013) carried out studies onmodifying strength pavement of bitumen using fibres. Nihat (2013) investigated on usability of basalt fibre in hot mix asphalt concrete. Olumide (2014) explained Performance of Glass Fibre with bitumen emulsion to delay the cracking on surface of the pavement . Yuanxun (2014) identified Fatigue Property of Basalt Fibre in modified asphalt mixture under Complicated Environment. Midhila (2015) carried a comparative study of bitumen modification using synthetic and natural fibre. Sateesh (2017) evaluated Performance Of Basalt Fibre Modified Bitumen In Dense Bitumen Macadam. Harsha(2017) carried partial replacement of bitumen with glass fibre in flexible pavement .the





ISSN 2348 - 8034 Impact Factor- 5.070

result indicate that by addition of glass fibre the penetration value increased as compared to the nominal mix. Yongchun ,(2017) carried research facility Study on Properties of Diatomite and Basalt Fiber Compound Modified Asphalt Mastic .The present study is focused on improving the characteristics with binder modification through inclusion of PPA and reinforcement of modified mixture using fibre.

Acid Modification by using Polyphosporic acid (PPA)

Source- Ylidizel (2017).

PPA, a medium solid corrosive (Hammet causticity work = 6, sulfuric corrosive $H_2SO_4 = 12$), is an inorganic polymer, all the more explicitly an oligomer, gotten by buildup of monophosphoric corrosive or by hydration of phosphorous pentoxide (P_2O_5) from TRC

(2012).



Figure. 1 Influence of PPA on the colloidal structure of bitumen

Source- Catarina(2016)

The reactivity of PPA increments with the extremity of the asphaltene portion since it upgrades PPA separation (into PPA- and H+) [3] upsetting the hydrogen security arrange framed inside the agglomerates of asphaltene micelles. Therefore, the atomic weight of the asphaltene portion is brought down and the appropriation of asphaltenes in the rest of the parts is enhanced, moving the bitumen towards a more flexible gel-type structure, as shown in Figure 1.

Fibre

Fibre is used as reinforcement in modified mix. In this study glass fibre is used and the properties are tabulated in table I.

TABLE I Glass fibre properties			
Description	Value		
Ultimate strength, bending (MPa)	20-28		
Elastic limit, bending (MPa)	7-11		
Ultimate strength, tensile (MPa)	8-11		
Elastic limit, tensile (MPa)	5-7		
Compressive Strength (Mpa)	50-80		
Elastic Modulus (GPa)	10-20		

63

II. METHODOLOGY

The sequence of stages was followed in achieving the objectives of study

- Stage 1: Literature review study
- Stage 2: Aggregate gradation selection

Stage 3: Marshall Mix design for Conventional mix, modified and fibre reinforced mixes

Stage 4: Evaluating the Tensile strength, Resilient Modulus and Rutting for above mix combination





ISSN 2348 – 8034 Impact Factor- 5.070

III. EXPERIMENTAL PROGRAMME

In order to meet the objective of study following experimental process is adopted as per ASTM MORTH guidelines.

a) Aggregate Gradation

Bituminous concrete (BC) mix of grade -I with nominal maximum aggregate size of 19mm is used in the study as per MORTH specifications. The selection of percentages of different ingredients for preparation of BC mix of Grade -I study is shown in Figure 2.



Figure. 2 Gradation of Aggregate

b) Materials

The materials used for this study are aggregates, bitumen (VG-30), polyphosporic acid(PPA), glass fibre(12mm length) chopped. Crushed aggregates were collected from local quarry of Hyderabad city, Telangana State, VG 30 grade bitumen was collected from the Vishakhapatnam provided by (IOCL).PPA Polyphosporic acid of reagent grade, 115% H₃PO₄ basis and glass fibres were collected from dwarikamai agency near koti Hyderabad. Initially physical properties of aggregates (as per IS 2386) were determined. Crushing, impact, hardness, specific gravity, water absorption and elongation and flakiness indices (combined) are performed. Physical properties of bitumen carried out.

c) Modified Binder

Binder modification has carried by introducing PPA to the virgin binder at an increment of 1%. The rheological properties of modified binder was studied using Dynamic Shear Rheometre DSR and is depicted in fig. 3.The dynamic shear rheometer test is a measure of consistency and flexible properties of black-top mastic at medium and high temperature. (ASTM D7175), the tests were performed by a parallel plate that had a hole of 1.0mm and distance across of 25mm. The modified bitumen was placed between two parallel plates; the base plate was settled. The upper plate was swayed at a stacking recurrence of 10rad/s (1.59Hz). Rutting and fatigue parameter is arrived for the adjusted cover. In this study five sample were taken to know the rheological properties of binder with PPA.





ISSN 2348 - 8034 Impact Factor- 5.070



Figure. 3 Dynamic shear rheometer

d) Preparation of specimen(Marshall specimen)

Around Around 1200gm of totals blend is required for readiness of BC blend sample. The dry blend of totals and filler material is preheated to test temperature of 135C and bitumen is included proportionately. Mix arrangement was finished by incorporation of PPA using stirrer shown in fig 4. The response time is normally short. The run of the mill lab test is set up by including the coveted measure of PPA to a bitumen sample at 149°C, and mixing improved the situation no less than 30 minute. When an objective plan has been created, lab mixes ought to be assessed for all particulars and whole blend is set up at temperature of 135° C. The mix is placed in 100 diameter mould and compacted by rammer of weight 4.54kg for 75 blows on each side. The height of fall of rammer is 45.7 cm and compaction is carried through automatic compactor. The compacted specimen should have a thickness of 63.5 mm. This test is conducted in accordance with ASTM D6927 - 15. The Marshall test is used to determine the optimum binder content for the mix. A progression of test samples was set up for a scope of various cover content (4-6) as determined in MORTH for BC blend. The elements of the test examples were 100 mm in breadth and 63.5mm in tallness with an objective void substance of 4%. Three test examples were compacted for every level of cover content; altogether 69 specimens were used to arrive the Marshall parameters. The Marshall Stability and flow test gives the forecast measure to the Marshall blend structure technique. The stability parts estimates the greatest load upheld by the test sample at a loading rate of 50.8 mm/minute. Load is connected to the sample till it comes up short, and the most extreme load is considered as dependability. At the loading time, an appended dial check estimates the specimen plastic stream (deformation) because of the loading. The flow esteem is recorded in 0.25 mm (0.01 inch) augments in the meantime when the greatest load is recorded. Following setup shown in Fig.5.



Figure. 4 Magnetic Stirrer 65



(C)Global Journal Of Engineering Science And Researches



ISSN 2348 - 8034 Impact Factor- 5.070



Fig. 5 Marshall Stability apparatus

e) Indirect tensile strength test

Where, IDT = indirect tensile strength test; P = failure load; t = thickness of specimen d = diameter of specimen. Three test specimens were prepared from the obtained optimum result first specimen is of conventional mix, remaining specimen is of modified mixes with glass fibre using additive as PPA in binder.



Figure.6 IDT set-up with sample & on Line D

f) Resilient Modulus Test

The resilient modulus is the elastic modulus based on the recoverable strain under repeated loads. It provides a means of characterizing pavement construction materials co pare the behaviour of pavement construction materials under a variety of conditions. However, if the strength of the material is large as compare with load and is applied repetitively, the deformation under each loads application completely recoverable and proportional to the load which gives the elastic behaviour of material. ASTM D7369-11 standard code to determine the resilient modulus of bituminous mixes by indirect tension test. In this test a linear force along the diameter axis of the specimen is applied as shown in Fig.5.. Each loading cycle was 0.1s long. Thus, given the total duration of loading and





ISSN 2348 - 8034 Impact Factor- 5.070

unloading of 1 s, the rest time period of each cycle is 0.9s. The scale of load applied was 10% of tensile strength obtained from IDT at 350°C. The rigidity modulus for cylindrical specimens is determined as

MR=P(0.27+ μ) / t. Δ h Equation (2)

Where, MR= Resilient modulus (MPa); P = Repeated load (N); μ = Poisson's ratio, t= Thickness of HMA sample (mm); Δh = Horizontal deformation (mm). One samples for each mix with a total of 3(virgin mix, glass, fibre and basalt fibre) were tested along the diametrical plane to calculate strain and modulus parameters



Fig.7 Repeated load instrument

g) Specimens for Rutting

The specimen is composed in a slab compactor also known as roller compacting device shown in Fig 3.4(a) its volume is of around 6000 cc. The specimens were set up with densities gratified base from Marshall Stability test. The specimens were compacted using hydraulic pressure in oscillatory motion. When the desired densities of blend are accomplished as clarified in (BS EN 12697 33) at that point the compaction has been stopped. In this research three slab with different mix were prepared (conventional mix, Modified mix of glass and basalt fibre with PPA) with total weight of mix 13.5 kgs in which filler amount consist of 732.9 gms and 717 gms of bitumen.

h) Immersion type of wheel tracking device

In the present research, an augmented test replicated in the laboratory for estimation of rutting resistance was used and is presented through Fig.3.The wheel utilised in the analysis is steel wheel of 47 mm wide and the total weight of the wheel with surcharge is 710N.To measure rut depth LVDT is used. Specimens were tested in soaked condition at a temperature of 50oC. Immersion test is carried for understanding the strip off obstacle of mixes. The moment of the wheel path is 230 mm and the speed of the wheel for one pass is nearly1.46 kmph (72 wheel passes per min). B.C grade I as per MORTH is adopted for the present investigation in preparation of specimens. 24102 passes will simulate traffic of 30 msa in the field (Nahi, 2011).



Figure.8 Immersion type of wheel tracking device





IV. RESULTS

a) Physical properties of aggregates and bitumen

Aggregates and bitumen test were conducted for the preparation of adopted mixes. Aggregates test as per MORTH specification to find the strength ,hardness, shape etc , where as bitumen test is to find the grade of bitumen as per IS:73:2016 shown below ,Table II and Table III.

TABLE II Enysical properties of aggregates					
TEST CONDUCTED	LABORATORY RESULTS (%)	MORTH SPECIFICATION	TEST STANDARDS		
Aggregate crushing value	23	Max 30	IS:2386(IV)		
Aggregate Impact Value	20	Max 30	IS:2386(IV)		
Elongation index	12.45	<15	IS:2386(I)		
Flakiness index	12.32	<15	IS:2386(I)		
Water absorption	0.4	0.1-2	IS:2386(III)		
Specific Gravity	2.6	2-3	IS:2386(III)		
Los Angeles abrasion value	23	Max 30	IS:2386(IV)		

TABLE II Physical properties of aggregates

TABLE III Physical properties of Bitumen

CONSISTENCY	VC 20	SPECIFICATIONS OF	TEST
CHARACTERISTICS	VG-30	VG-30	STANDARDS
Penetration at 25 [°] C	55	50-70	IS:1203
Softening point(⁰ C)	47.5	Min 47	IS:1205
Ductility(cm)	50.33	Min 50	IS:1208
Absolute Viscosity (Poise)	2567	Min 2400	IS:1206(II)
Kinematic Viscosity ((cSt)	358.67	Min 350	IS:1206(II)

From the table results of aggregate and binder obtained as per MoRT&H guide lines for BC-1 mix and IS 73:2016 for binder properties.

b) Modified Binder

The rheological parameters dynamic shear rheometer test was conducted on the modified binder samples, test results are as presented in Table IV. The test was conducted under stress controlled mode at a frequency of 10 rad/s. and at a constant temperature of 135 $^{\circ}$ C

TABLE IV Re.	sults Of Dynar	nic Shear Rheometr	e
--------------	----------------	--------------------	---

MEAN INTERVALS	PHASE ANGLE δ	COMPLEX MODULUS G* (Pa)	STRAIN (%)	G*/SIN δ (RUTTING PARAMETER) KPa	G* SIN δ (FATIGUE) KPa
P1	83.9	1.29E+04	12.1	14.142	13.828
P2	83.6	1.48E+04	13.3	10.9	12.314
P3	84.5	1.15E+04	14.1	9.24	9.56
P4	84.7	1.12E+04	15.1	10.68	10.585
P5	85.2	9.38E+03	15.1	9.86	9.781

68

From the test results is observed that 3% PPA has improved G*sino and G*/sino value.





c) Marshall Stability properties

TABLE V Sample Codes For Different Mixes

Suitable mix code was used for understanding the properties and is tabulated in table V

Mix No.	Description	Code
1	Conventional mix with virgin bitumen	Conv.
2	Conventional mix with glass fibre as an additive	CG
3	Conventional mix optimum with PPA as binder modifier	PPA
4	Modified bituminous mix with optimum of PPA along with glass fibre	CPPAG

Marshall Results of conventional mix is tabulated in table VI TABLE VI Marshall Results For Conventional Mix

Binder content (%)	Stability (kN)	Air voids (%)	Bulk density (g/cc)
4	4.655	6.545	2.353
4.5 7.242		3.645	2.166
5 9.398		3.251	2.243
5.5	11.005	3.218	2.152
6	4.782	3.106	2.067

The optimum binder content for the conventional mix is obtained at 5%. with stability is 11.005 kN as shown in Table VI. PPA was added at regular interval to OBC of virgin mix and the result is tabulated in table VII

PPA (%)	Stabality (kN)	Air voids (%)	Demsity(g/cc)
1	9.56	7.36	2.38
2	10.25	6.10	2.40
3	11.68	4.15	2.452
4	8.56	2.46	2.432
5	7.52	2.38	2.36

From table VII it is observed that PPA at 3% provides better Marshall Properties, this is because of improved gel type structure in mix combination. Based on the optimum PPA content in bitumen mix, glass fibre was added at 1,2,3,4, and 5% with weight of bitumen mix. The Marshall Results are depicted in fig 8.



Fig.9 Stability, Air voids and Density for different CG and CPPAG mixes

The stability of fibre added to PPA mix is higher compared with only fibre mix. From above graph, the air void is also improved for acid fibre mix which is having good structure and interlocking properties. The optimum result is tabulated in table VII.





ISSN 2348 - 8034 Impact Factor- 5.070

	Binder Content (%)				
ype	Max Stability 4% Volume Max Bulk Averag				
	(kN)	of Voids (%)	Density (gm/cc)	Content (%)	
V	5.5%	4.3	5%	5	
	2%	4.3	3%	3.1	
k.	3%	3	3%	3	
.G	2%	3.1	3%	2.7	

TABLE VIII Optimum Marshall Results For Mix Combinations

d) Tensile Strength Ratio (TSR)

HMA mix has reduction in adhesion property between the surface of aggregate and binder its susceptible to moisture damage. The ITS is conducted to evaluate the damages due to moisture takes place in bituminous mix. TSR ratio is a measure of water sensitivity. It is the ratio of the tensile strength of soaked specimen, (ITS wet, 60°C, and 24 h) to the tensile strength of un soaked specimen (ITS dry) which is expressed as a percentage.

TSR = S1/S2

S1 = Tensile Strength of soaked sample (MPa)

S2= Tensile Strength of un soaked sample (MPa)

The complete mix is said to perfect and having well resistance toward moisture damage only when the TSR value is high. The minimum of 0.70 to 0.80 . TSR is often used as a standard mentioned in ASTM D 4867.

Mixture Combination	Soaked (S1) MPa	Unsoaked (S2) MPa	TSR (S1/S2)
CONV	0.756	0.968	0.780
CG	0.862	1.045	0.824
CPPAG	0.959	1.064	0.901

TABLE IX Tensile strength ratio for different mix combination

The above result exhibit that CPPAG mix has better moisture susceptibility then other mix combination.

e) Resilient Properties

Repeated load test is performed to determine the resilient modulus for each combination. The results are shown in Table X.

TABLE X~ Repeated toda test results							
MIX	BINDER	LOAD	HORIZONTAL	TENSILE	RESILIENT	INITIAL	
	CONTENT %	(N)	DEFORMATION(MM)	STRESS	MODULUS	TENSILE	
				(MPA)	(MPA)	STRAIN (MM)	
CONV	5	950	0.006282	0.95	2416	0.000806	
CG	3.1	1045	0.004389	1.045	2587	0.000828	
CPPAG	2.7	1064	0.003585	1.064	2890	0.000754	

TABLE X~ Repeated load test results

f) Rutting behaviour

The rutting test is performed based on the standard of AASTHO- T 324 and used to the deformation behaviour of mix combination. In this paper three slabs were prepared at optimum binder cotent (OBC), optimum fibre content (OFC), optimum PPA content (OPPAC) and densities obtained from Marshall results. Bituminous mix prepared with glass fibre using PPA as an additive shows best result when compared with other mixes presented in Fig.9.





ISSN 2348 - 8034 Impact Factor- 5.070



Fig.10 Rutting characteristics for different mix combinations

CPPAG mix provides better resistance towards rutting than other mix combination. This because of gel-type structure and improved void ratio results in rutting resistance for same number of wheel passes.

V. CONCLUSIONS

The following summary and conclusion are drawn from study: Complex modulus and fatigue properties enhanced with addition of PPA when compared to conventional binder. Marshall properties were improved in CPPAG mix because of gel-type structure in PPA. ,There is an improvement in moisture susceptibility, resilient property and resistance toward rutting for CPPAG mix combination. Hence acid modification with fibre provides better performance characteristics than conventional mix.

REFERENCES

- 1. Abdul khaedar, 'a laboratory study on acid modified bituminous mixes in comparison for rutting characteristics", Journal of Civil Engineering and Urban Planning, Vol no- 04,2015.
- 2. Fan Wenxiao, 'Laboratory study of marshall of basalt fibre modified asphalt mixture". Trans Tech publication, Switzerland, Journal of applied mechanics and materials, vol no-:256-259,pp-:1851-1857,2012.
- 3. Ghorpade, Desai D, " A Study of Enhancement of Bituminous Mix by Use of Modifiers", Imperial journal of interdisciplinary rsearch, vol-4,2018.
- 4. Harsha, Nikhil, '' Partial replacement of bitumen with glass fibre in flexible pavement" International journal of civil engineering and technology, vol no-:08, pp-: 1176-1181,2017.
- 5. Midhila, "Comparative study on bitumen modification using synthetic and natural fibre". International research journal of engineering technology vol no::04,pp::2395-0072,2017.
- 6. Nihat Morova, "Investigation of usability of basalt fibre in hot mix asphalt concrete", Journal of construction and building materials, vol no-:47, pp-:175-180, 2013.
- 7. Ogundipe, Ekiti state university, Nigeria, ''Investigation of performance of glass fibre impregnated with bitumen emulsion against reflective cracking", Journal of civil and environmental engineering, vol no-:4, pp-:2165-784X, 2014.
- 8. Ramesh.A, ''Evaluation of rutting characteristics in stone mastic asphalt mix when added with basalt fibre''. *i-managers*, Journal on material science, 4(3), 19-26, 2016
- 9. Sateesh.P , Avinash , ''A study on the performance of glass fibre modified bitumen in dense bitumen macadam", International journal of advanced in management, vol no-:07, pp-:2249-7455, 2017.
- 10. Yuanxun, College of water conservancy and environment, China, 'Fatigue property of basalt fibre modified asphalt mixture under complicated environment", Journal of Wuhan university of technology material science, vol no -: 29,2014
- 11. Yongchun, Zehua ,College of Transportation, Jilin University, China, 'Laboratory study on properties of Diatomite and Basalt fiber compound modified asphalt mastic", Journal of advanced in materials science and engineering,2017





ISSN 2348 - 8034 Impact Factor- 5.070

- 12. Standard Test Method for conduct of Resistance to Plastic Flow of Bituminous Mixtures Using Marshall Apparatus ASTM D5581 07a (2013)
- 13. Standard Test Method for conduct of Indirect tensile strength test- ASTM D4123 82(1995)
- 14. Standard Test Method for conduct of Resilient Modulus Testing of Asphalt specimens-ASTM D 4123 82(1990)
- 15. Standard Test Method for Measuring Rut-Depth of Pavement Surfaces Using a Straightedge- ASTM E1703 / E1703M 10(2015)
- 16. Standard Test Method for Determining the Rheological Properties of Asphalt Binder Using a Dynamic Shear Rheometer- ASTM D7175 - 15
- 17. IRC SP 53, guidelines on use of modified bitumen in road construction.

